

# Rylard Slip Resistance Kit

<p><b>Product Description</b></p>	<p><b>A smooth fine aggregate powder</b>, designed for addition to Rylard Plus Enamel or Rylard Raddle to produce an anti-slip finish.</p>
<p><b>Features &amp; Use</b></p>	<ul style="list-style-type: none"> <li>• Suitable for the upper deck areas and walkways of canal boats and leisure craft</li> <li>• Supplied as loose powder in a 750ml tin</li> <li>• <b>Recommended method of application</b> is to apply a Rylard topcoat and while still wet, sprinkle the surface with powder aggregate and allow to dry. When dry, sweep off excess powder. Take care to apply an even scattering of powder – scattering using of a sieve may help. A second coat of Rylard finish may then be applied (when dry and swept) if required.</li> <li>• Alternatively, <b>gradually</b> add 1 x 750ml of Rylard Plus Enamel paint to the can containing the powder, and mix constantly and thoroughly while doing so, to ensure as even a distribution of the powder as possible.</li> <li>• It is recommended that the paint/anti-slip mixture is applied by brush, but a much better finish is usually obtained by applying the paint neat, and scattering the powder on while wet, as described above.</li> <li>• If a lower degree of anti-slip is required, add less than the full amount of powder. If more anti-slip is needed, add powder from a second tin of Slip Resistance Kit, to the required level of anti-slip, up to a maximum of 2 Kits per 750ml of Rylard Plus Enamel.</li> </ul>
<p><b>Product Code</b></p>	<p><b>15SRK-000-60G</b></p>
<p><b>Health &amp; Safety</b></p>	<p>Containers are provided with safety labels which should be observed. Further information about hazardous influences and protection are detailed in individual Product Safety Data Sheets. A Safety Data Sheet for this product is available on request from Rylard Paints.</p>

AN AXALTA COATING SYSTEMS BRAND



The information provided herein corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since Axalta cannot anticipate all variations in actual end-use conditions Axalta makes no warranties and assumes no liability in connection with any of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. This product is for professional use only.